



Pinnacle Polymers LLC

1 Pinnacle Ave
PO Box Drawer E
Garyville, LA 70051 United States

File Number: E130336

32(a)

Polypropylene (PP), pellets or powder

(a) - any number, 4-20 inclusive, denoting melt flow



Flammability	Value	Test Method
Flame Rating		
0.75 mm, NC	HB	UL 94
1.5 mm, NC	HB	UL 94
3.0 mm, NC	HB	UL 94
3.0 mm, NC	HB40	IEC 60695-11-10, -20
0.75 mm, NC	HB75	IEC 60695-11-10, -20
1.5 mm, NC	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec		UL 746B
0.75 mm	110 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
RTI Imp		UL 746B
0.75 mm	110 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
RTI Str		UL 746B
0.75 mm	110 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	